

PERMABOND® 4UV80HV

UV-Curable Adhesive for Medical Devices

Technical Datasheet

Features & Benefits

- Cure on demand
- High shear strength
- Fast curing with low-power lamps
- 100% solids, no solvents
- Excellent adhesion to medical plastics

Biocompatibility	
ISO 10993-5 Cytotoxicity	

Description

PERMABOND® 4UV80HV is a single part, fast setting, and UV curable adhesive designed specifically for bonding medical devices. It has excellent adhesion to a variety of plastics and metals commonly found in the medical industry.

Physical Properties of Uncured Adhesive

Chemical composition	Methacrylate ester
Appearance	Opaque / translucent Clear when cured
Viscosity @ 25°C	1800-2800 mPa.s (cP)
Specific gravity	1.1
Flashpoint	100°C

Typical Curing Properties

Fixture time (low power 4mW lamp)*	Polycarbonate: 55 seconds
	Acrylic: 6 seconds
	PVC (rigid): 6 seconds
	PVC (flexible): 5 seconds
	PC to ABS: 55 seconds
Cure wavelength	365 - 400 nm**


^{*}The cure time depends on the power of the UV lamp, its spectral output, the distance between the lamp and the components, and the transmission characteristics of the substrates. The cure time quoted here was determined using a low power, hand held lamp. Most industrial UV lamps would give faster cure rate.

Typical Performance of Cured Adhesive

Overlap shear strength (ISO4587)	Polycarbonate: >9 N/mm² * (>1300 psi) PVC (rigid): >5MPa * (>700psi) PVC (flexible): >2.5MPa * (>400 psi) PC to ABS: >9MPa * (>1300 psi)
Tensile strength (ISO37)	12 N/mm² (1700 psi)
Impact Strength	4-9.5 J
Elongation at break (ISO37)	20%
Hardness (ISO868)	60 Shore D
Dielectric strength	12 KV/mm
Dielectric constant 1MHz@25°C	4

^{*}Substrate failure was observed

Strength results will vary depending on the level or surface preparation and gap.



"Hot strength" shear strength tests performed on glass to mild steel. Fully cured specimens conditioned to pull temperature for 30 minutes before testing at temperature.

4UV80HV can withstand higher temperatures for brief periods (such as for paint baking and wave soldering processes) providing the joint is not unduly stressed. The minimum temperature the cured adhesive can be exposed to is -55°C (-67°F) depending on the materials being bonded.

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.

Permabond 4UV80HV Global TDS Revision 2 20 March 2019 Page 1/2

^{**}LED UV lamps have a narrow range of spectral output. It is important to check suitability with Permabond in order to match the LED lamp's peak wavelength with that of the adhesive's photoinitiator to ensure optimal adhesive cure.

Additional Information

This product is not recommended for use in contact with strong oxidizing materials.

Information regarding the safe handling of this material may be obtained from the Safety Data Sheet.
Users are reminded that all materials, whether innocuous or not, should be handled in accordance with the principles of good industrial hygiene.

This Technical Datasheet (TDS) offers guideline information and does not constitute a specification.

Surface Preparation

Surfaces should be clean, dry and grease-free before applying the adhesive. Particular care should be taken to remove silicone based cleaning agents which may have been used previously to clean glass.

Some metals such as aluminium, copper and its alloys, will benefit from light abrasion with emery cloth (or similar) to remove the oxide layer.

Isopropanol can be used to degrease most surfaces. Where thermoplastic surfaces are involved we recommend tests are done to ensure compatibility, mold release agents may affect bond strength.

Directions for Use

- 1) Adhesive can either be applied directly from the bottle or dispensed via automated dispensing equipment for more accurate dosing. Minimise exposure of product to ambient light.
- 2) It is important to try to prevent air entrapment within the joint as this could be detrimental to the finished appearance of the adhesive.
- 3) Parts should be firmly held and not disturbed during cure. Expose the joint to ultra-violet light for the appropriate time to ensure full cure. Cure time depends on the power of the UV lamp, its spectral output, the distance between the lamp and the components, and the transmission characteristics of the substrates.
- 4) For help selecting a suitable lamp and/or dispensing equipment, please contact the Permabond technical helpline.

Video Link

UV adhesive directions for use: https://youtu.be/Y9q0FGFhdvc



Other Products Available

Anaerobics

- Thread lockers Thread sealants
- Gasket makers Sealants / retainers

Cyanoacrylates

- Instant adhesives
- For rapid bonding of metals, plastics, rubber and many other materials

Epoxies

- Two-part room temperature cure adhesives
 - Single-part heat cure adhesives
- Modified Technology (MT) flexible grades available

MS-Polymers

Single-part, moisture-curing, flexible sealants

Polyurethanes

■ Two-part room temperature curing adhesives

Toughened Acrylics

Rapid curing, high strength structural adhesives

UV Light Cured Adhesives

- Glass / plastic bonding
 - Optically clear
 - Non-yellowing

Storage & Handling

Storage Temperature 5 to 25°C (41 to 77°F)

Protect liquid adhesive from room lighting.

www.permabond.com

• UK: 0800 975 9800

• General Enquiries: +44 (0)1962 711661

• US: 732-868-1372

• Asia: + 86 21 5773 4913

info.europe@permabond.com info.americas@permabond.com info.asia@permabond.com

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.

Permabond 4UV80HV Global TDS Revision 2 20 March 2019 Page 2/2